



The Radiance Collection

Grade 3 Crypton



FLUX

Available in 15 vibrant colors.



1005578 Cayenne



1005196 Gecko



1005197 Leaf



1005198 Biscuit



1005199 Maple



1005200 Ivy



1005201 Tempest



1005202 Nugget



1005203 Jadeite



1005204 Coffee



1005205 Copper



1005206 Danube



1005207 Ebony



1005208 Cabernet



1005209 Dutch Boy

BELLA

Available in 14 vibrant colors.



1005257 Beige



1005210 Chive



1005211
Mascarpone



1005212
Basil



1005213
Ibiza



1005214
Buff



1005215
Smoke



1005216
Storm



1005217
Toast



1005218
Toffee



1005219
Persimmon



1005220
Latte



1005221
Sepia



1005222
Chili

BIANCA

Available in 13 vibrant colors.



1005223 Blood Orange



1005224
Snow



1005225
Sea Mist



1005226
Herb



1005227
Buff



1005228
Camel



1005229
Star Fruit



1005230
Fawn



1005231
Russet



1005232
Sprig



1005233
Chestnut



1005234
Ink



1005235
Winter

BIJOU

Available in 21 vibrant colors.



CRYPTON®
Super Fabrics



1005236 Tropic



1005237 Star Fruit



1005238 Herb



1005239 Butterscotch



1005240 Sea Mist




1005241 Snow



1005242 Camel



1005243 Terra



1005244 Storm



1005245 Buff



1005246 Black Pearl



1005247 Blood Orange



1005248 Sprig



1005249 Fawn



1005250 Chestnut



1005251 Garnet



1005252 Ivy



1005253 Russet



1005254 Ink



1005255 Majesty



1005256 Cadet

THE RADIANCE COLLECTION

FLUX

Available in 15 Colors

Specifications

Contents 100% Polyester

Width 54"

Performance

Stain Resistance,
Class 4-5

Lightfastness AATCC 16,
Class 4.0 after 40 Hours

Crock AATCC 8,
Class 4.0 wet

Abrasion Resistance ASTM D 4157
Exceeds over 100,000 double rubs
cotton duck

Suter AATCC 100,
100cm average

Tear ASTM D 2261,
13 lbs. Warp,
25.1 lbs. Fill

Tensile ASTM D 5034,
135 lbs. Warp,
198 lbs. Fill

Resistance to Fungi AATCC
147-1998, Excellent Properties

Seam Slippage
ASTMD 4034,
78 lbs. Warp,
84 lbs. Fill

BELLA

Available in 14 Colors

Specifications

Contents 100% Polyester

Width 54"

Performance

Stain Resistance,
Class 4-5

Lightfastness AATCC 16,
Class 4.0 after 40 Hours

Crock AATCC 8,
Class 4.0 wet

Abrasion Resistance ASTM D 4157
Exceeds over 50,000 double rubs
cotton duck

Suter AATCC 127,
100cm average

Tear ASTM D 2261,
8.5 lbs. Warp,
6.5 lbs. Fill

Tensile ASTM D 5034,
346 lbs. Warp,
276 lbs. Fill

Resistance to Fungi AATCC
147-1998, Excellent Properties

Seam Slippage
ASTMD 4034,
95 lbs. Warp,
98 lbs. Fill

BIANCA

Available in 13 Colors

Specifications

Contents 100% Polyester

Width 54"

Performance

Stain Resistance,
Class 4-5

Lightfastness AATCC 16,
Class 4.0 after 40 Hours

Crock AATCC 8,
Class 4.0 wet

Abrasion Resistance ASTM D 4157
Exceeds over 100,000 double rubs
cotton duck

Suter AATCC 127,
100cm average

Tear ASTM D 2261,
9.1 lbs. Warp,
18.9 lbs. Fill

Tensile ASTM D 5034,
499 lbs. Warp,
305 lbs. Fill

Resistance to Fungi AATCC
147-1998, Excellent Properties

Resistance to Bacteria AATCC 30,
Excellent Properties

Seam Slippage
ASTMD 4034,
109 lbs. Warp,
109 lbs. Fill

BIJOU

Available in 21 Colors

Specifications

Contents 100% Polyester

Width 54"

Performance

Stain Resistance,
Class 4-5

Lightfastness AATCC 16,
Class 4.0 after 40 Hours

Crock AATCC 8,
Class 4.0 wet

Abrasion Resistance ASTM D 4157
Exceeds over 100,000 double rubs
cotton duck

Suter AATCC 127,
100cm average

Tear ASTM D 2261,
41.4 lbs. Warp,
26.1 lbs. Fill

Tensile ASTM D 5034,
502 lbs. Warp,
368 lbs. Fill

Resistance to Fungi AATCC
147-1998, Excellent Properties

Seam Slippage
ASTMD 4034,
81 lbs. Warp,
78 lbs. Fill

Flammability

Passes California 191-53 Technical Bulletin 117 Section E. Passes NFPA 260;
UFAC Class 1.



Crypton, Inc. 6745 Daly Road, West Bloomfield, MI 48322

Crypton is protected by nine global patents—U.S. Patents 6,541,138, 6,492,001, 6,251,210, 6,207,250, 6,165,920, 6,024,823, 5,747,392, 5,565,265, and 6,884,491—Other U.S. and International Patents pending.

Crypton is a registered trademark of Crypton, Inc.